

**Technical Data Sheet** 

Product: PLASPAINT CRACKLE EFFECT

Reference: PP-SE-CRAC

# Description

PlasPaint Crackle Effect is a pre-blended ready to use paint that is easily applied using a conventional spray gun. It is available in a range of colours such as black, gold, white, copper and silver. Crackle Effect Spray Paint is applied over a contrasting colour. As the crackle effect dries the surface fractures revealing the contrasting base colour below. PlasPaint Crackle is a Pre-Mixed industrial quality highly versatile Polyurethane Acrylic paint specifically

formulated to provide outstanding performance on a variety of substrates.

#### **Recommended Substrates**

composite doors, glazing cassettes, uPVC windows, steel and aluminium

#### Features and Benefits

Excellent Surface Adhesion | UV stable and weather resistant | Excellent scratch resistance

Excellent chemical resistance | Can be machined after cure | Any colour base coat | Various top coat colours

# Mixing and Application

- 1. Take Crackle A and stir well, add 14% of UT pigment for desired colour.
- 2. Apply material using gravity fed spray gun approx. 120g/M2 & leave 20minutes to dry
- 3. Take Crackle B stir well making sure it is a contrasting colour to Crackle A and apply using gravity fed spray gun. Allow time for the crackle effect to work
- 4. Apply a protective topcoat using PlasPaint matt or gloss base with catalyst.

All substrates must be prepared using CR degreaser or foil safe degreaser. For PVCu use a fine scouring pad dipped in water and lightly rub the surface of the white profile creating a very fine surface key. Wipe dry with a soft tissue and then using a soft cloth wipe the surface clean using CR degreaser before applying Plaspaint Crackle Effect.

### **Chemical Properties**

Product density:  $1,01 \text{ g/cm}3 \pm 0,010 \text{ at } 200\text{ C}$ 

Colour: Various

Product viscosity: 35sec ± 3sec Cup: FORD 4 Application viscosity: 25sec ± 5sec Cup: FORD 4 Touch dry at 20oC: 30 minutes Total dry at 20oC: 6 hours Mixture Pot-life: 4 hours

Unit 17C, Upper Field Road, Sittingbourne, Kent, ME10 3UP UK



info@creative-resins.co.uk



www.creative-resins.co.uk



00 44 (0) 1795 411 820

