



#### Description

Granite spray effect resembles the aesthetic of granite stone. The product contains small black or white particles that can be intermixed. They are ideal for use on splashbacks and kitchen or bathroom glass surfaces. Granite Effect is simply added to GlassPaints Supreme Base and Hardener and applied by conventional spray equipment onto a variety of substrates especially Glass including Toughened / Tempered Glass. The products are industrial grade and are chemically curing. They are non-isocyanate. They create long term weatherproof and UV stable coatings and achieve excellent scratch and chemical resistance and provide a permanent bond to the substrate surface, especially glass. The Granite effect is normally backed with a contrasting solid colour. It can be used internally or externally and is heat and water repellent.

#### Recommended Substrates

Glass, Toughened / Tempered Glass. Laminated Glass

#### Features and Benefits

Excellent Surface Adhesion | UV stable and weather resistant | Excellent scratch resistance | Excellent chemical resistance | Suitable for domestic, commercial and industrial application | Available with Black or White particles| High Gloss finish

#### Mixing and Application

Cleaning: Clean the glass thoroughly with CR Glass Cleaner.

Mix: add 10-20% of the Granite effect solution into equal amounts of the GlassPaints Transparent Supreme base & hardener. The granite effect is then backed in a contrasting colour using GlassPaints Supreme which highlights the small white or black particles creating that real granite stone look.

#### Chemical Properties

Product Material: Acrylic and Epoxy

Colour: Translucent

Product viscosity: 24sec  $\pm$  1-5sec Cup:

FORD 4

Solids content: +55%

Touch dry at 20°C: 10 minutes

Total dry at 20°C: 1 hour

Full Cure: 7 days

Unit 17C, Upper Field Road, Sittingbourne, Kent, ME10 3UP UK

✉ [info@creative-resins.co.uk](mailto:info@creative-resins.co.uk)

🌐 [www.creative-resins.co.uk](http://www.creative-resins.co.uk)

☎ 00 44 (0) 1795 411 820



